



# AEROSPACE MATERIAL SPECIFICATION

AMS2478™

REV. F

Issued 1957-09  
Reaffirmed 2018-08  
Revised 2023-12

Superseding AMS2478E

## Anodic Treatment of Magnesium Alloys Acid Type, Full Coat

### RATIONALE

AMS2478F results from a Five-Year Review and update of this specification with the addition of Ordering Information notice, addition of Fixture/Electrical Contact Locations (see 3.3.3) per GA, clarification of Coating Thickness (see 3.5.1), and changing lot definition per GA (see 4.3).

### NOTICE

**ORDERING INFORMATION:** The following information shall be provided to the plating processor by the cognizant engineering organization:

1. Purchase order shall specify not less than the following:
  - AMS2478F
  - Quantity of pieces to be plated
  - Magnesium alloy to be plated
  - Optional: Fixture/Electrical contact locations, when not specified (see 3.3.3)
2. Parts manufacturing operations such as heat treating, forming, joining, and media finishing can affect the condition of the substrate for treatment or, if performed after treatment, could adversely affect the treated part. The sequencing of these types of operations should be specified by the cognizant engineering organization or purchaser and is not controlled by this specification.

### 1. SCOPE

#### 1.1 Purpose

This specification establishes the engineering requirements for producing an acid-type, anodic coating on magnesium alloys and the properties of the coating.

#### 1.2 Application

This process has been used typically to increase corrosion and abrasion resistance and to provide surfaces which will improve paint adhesion, but usage is not limited to such applications.

SAE Executive Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2023 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system, or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)

Tel: +1 724-776-4970 (outside USA)

Fax: 724-776-0790

Email: [CustomerService@sae.org](mailto:CustomerService@sae.org)

<http://www.sae.org>

For more information on this standard, visit

<https://www.sae.org/standards/content/AMS2478F>

SAE WEB ADDRESS:

1.2.1 This process is applicable to all magnesium alloys provided proper allowance is made for dimensional change. It should not be used on parts which will be flexed in service. Abrasion resistance is not as high as that provided with the alkaline electrolytic treatment of AMS2476 but, when similarly painted or coated, other properties are equivalent. AMS2478 coatings often exhibit poor adhesion to surfaces of castings. Thin coatings in accordance with AMS2479 are preferred for castings.

### 1.3 Safety - Hazardous Materials

While the materials, methods, applications, and processes described or referenced in this specification may involve the use of hazardous materials, this specification does not address the hazards which may be involved in such use. It is the sole responsibility of the user to ensure familiarity with the safe and proper use of any hazardous materials and to take necessary precautionary measures to ensure the health and safety of all personnel involved.

## 2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

### 2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA), [www.sae.org](http://www.sae.org).

AMS2476      Electrolytic Treatment for Magnesium Alloys, Alkaline Type, Full Coat

AMS2479      Anodic Treatment of Magnesium Alloys, Acid Type, Thin Coat

AMS4352      Magnesium Alloy, Extrusions, 5.5Zn - 0.45Zr (ZK60A-T5), Precipitation Heat Treated

ARP4992      Periodic Test for Processing Solutions

AS7766      Terms Used in Aerospace Metals Specifications

### 2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, [www.astm.org](http://www.astm.org).

ASTM B244      Measurement of Thickness of Anodic Coatings on Aluminum and Other Nonconductive Coatings on Nonmagnetic Basis Metals with Eddy-Current Instruments

ASTM B487      Measurement of Metal and Oxide Coating Thickness by Microscopical Examination of Cross Section

### 2.3 Terms used in AMS are defined in AS7766.

## 3. TECHNICAL REQUIREMENTS

### 3.1 Solutions

#### 3.1.1 Electrolyte

Shall be an aqueous solution of one of the compositions shown in Table 1, maintained within the temperature range 175 to 185 °F (79 to 85 °C). If the type of current is not specified, either alternating current (AC) or direct current (DC) may be used. Alternative processing solutions may be used if acceptable to the cognizant engineering organization.

**Table 1A**

Ingredient	AC Process Quantity	DC Process Quantity
Ammonium Bifluoride, ounces (Avdp) per gallon ( $\text{NH}_4\text{F}\cdot\text{HF}$ )	30.0 to 60.0	40.0 to 60.0
Sodium Dichromate, ounces (Avdp) per gallon ( $\text{Na}_2\text{Cr}_2\text{O}_7\cdot2\text{H}_2\text{O}$ )	6.7 to 16.0	6.7 to 16.0
Phosphoric Acid, fluid ounces per gallon (85% $\text{H}_3\text{PO}_4$ )	6.5 to 14.0	6.5 to 14.0

**Table 1B**

Ingredient	AC Process Quantity	DC Process Quantity
Ammonium Bifluoride, grams/L ( $\text{NH}_4\text{F}\cdot\text{HF}$ )	225 to 449	300 to 449
Sodium Dichromate, grams/L ( $\text{Na}_2\text{Cr}_2\text{O}_7\cdot2\text{H}_2\text{O}$ )	50 to 120	50 to 120
Phosphoric Acid, mL/L (85% $\text{H}_3\text{PO}_4$ )	51 to 109	51 to 109

### 3.1.2 Sealer

Shall be an aqueous solution containing 6 to 8 ounces/gallon (45 to 60 grams/L) of sodium tetrasilicate ( $\text{Na}_2\text{Si}_4\text{O}_9$ ) maintained at a temperature of 200 to 212 °F (93 to 100 °C).

### 3.2 Equipment

#### 3.2.1 Tanks

Shall be fabricated from a material or lined with a coating that is compatible with the anodizing bath and shall be equipped with temperature controls capable of controlling the bath temperature within specified limits.

#### 3.2.2 Fixtures

Wire, hooks, clamps, and racks used to suspend parts in the electrolyte, and which are in contact with the electrolyte shall be of magnesium or magnesium alloys, or from aluminum alloys containing magnesium (5000 or 6000 series). Such fixtures shall be protected with a suitable maskant at the electrolyte-air interface.

### 3.3 Preparation

#### 3.3.1 Masking

Parts which contain inserts other than 5000 or 6000 series aluminum alloys and parts not to be anodized all over shall be masked to seal off the non-magnesium or non-aluminum materials and the surfaces not to be anodized.

#### 3.3.2 Cleaning

Parts shall be pickled and cleaned as necessary to ensure that surfaces are free from water break.

#### 3.3.3 Fixture/Electrical Contact Locations

Tight fixture/electrical contact shall be maintained during the anodic treatment/conversion coating process, in order to prevent damage or contact arcing (burning) of parts, but small irregularities of coating at points of fixture/electrical contact, are acceptable. Parts shall, insofar as practicable, be hung to avoid gas entrapment during processing.

3.3.3.1 For parts that are to be anodized all over, and contact locations are not specified, contact locations shall be at the discretion of the processor.

3.3.3.2 For parts that are not to be anodized all over, and contact locations are not specified, locations shall be in areas on which coating is not required.

### 3.3.3.3 AC Processing

Parts shall be distributed on both electrodes so that the surface areas of the parts on each electrode are approximately equal.

### 3.3.3.4 DC Processing

Parts shall be distributed on one electrode with the other electrode being separate steel plates except as noted in 3.4.1.

## 3.4 Procedure

### 3.4.1 Processing

The cleaned and racked parts shall be immersed in the electrolyte (see 8.3.1). The parts shall be made the anode in the DC process, and, for this process, the tank may serve as the cathode if it is made of unlined steel. Alternating or direct current, as applicable, shall be applied and the voltage raised manually or automatically during processing to maintain the required current density. Current density shall be maintained so that, in a processing time of not more than 30 minutes, the total power input will be not less than that shown in Table 2.

**Table 2 - Power Input**

Type of Current	Total Power Input
AC Process	460 ampere minutes/square foot (82 A-second/m <sup>2</sup> )
DC Process	300 ampere minutes/square foot (54 A-second/m <sup>2</sup> )

3.4.1.1 Completion of processing is indicated by a uniform, dark green color, free from definite bare or light-colored areas except as permitted in 3.6, examined, while wet, after rinsing in cold water.

### 3.4.2 Sealing

When specified, immediately after coating and rinsing, parts not to be painted or which are to be only partly painted shall be immersed in the sealer solution (see 3.1.2) for approximately 15 minutes.

### 3.4.3 Rinsing and Drying

After anodizing, or after sealing when specified, parts shall be rinsed thoroughly in cold, running tap water, rinsed in clean, hot water, and dried.

## 3.5 Properties

The coating shall conform to the following requirements:

### 3.5.1 Coating Thickness

Coating shall result in a dimensional increase of 0.0009 to 0.0016 inch (23 to 41  $\mu$ m) per surface. Anodize thickness shall be determined on representative parts or specimens (see 4.3.3) in accordance with ASTM B244, ASTM B487, by direct micrometer measurements, or by other method acceptable to the cognizant quality organization.

### 3.5.2 Coating Weight

If the size or shape of parts is such that coating thickness cannot be determined accurately, determination of coating weight may be substituted for determination of thickness. Coating weight shall be 3.600 to 6.400 grams/square foot (38.75 to 68.89 g/m<sup>2</sup>), determined as in 3.5.2.1.

3.5.2.1 Weigh an oven dried coated part or a coated test specimen (see 4.3.3). Strip the coating in a fresh, sulfate-free solution containing approximately 40 ounces/gallon (300 g/L) of chromic acid. Repeat the immersion in the stripping solution until the weight difference between successive measurements is less than 1.0 milligram/square inch (0.155 mg/cm<sup>2</sup>). After each stripping operation, wash the part or test specimen with distilled water and oven dry thoroughly before weighing. Determine coating weight by subtracting the weight of the stripped specimen from the weight prior to stripping and dividing by the surface area.

### 3.6 Quality

Surfaces of coated parts, as received by purchaser, shall be uniform in texture and appearance except that dark striations on parts made of extruded AMS4352 magnesium alloy will be acceptable if no pitting is present. Powdery areas, laminations, excessive buildup, and darkening of corners and edges are not acceptable. There shall be no bare or definite light-colored areas except as approved by the cognizant quality organization.

## 4. QUALITY ASSURANCE PROVISIONS

### 4.1 Responsibility for Inspection

The processor shall supply all specimens for the processor's tests and shall be responsible for the performance of all required tests. Where parts are to be tested, such parts shall be supplied by purchaser. The purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the coating conforms to the requirements of this specification.

### 4.2 Classification of Tests

#### 4.2.1 Acceptance Tests

Coating thickness (see 3.5.1) or coating weight (see 3.5.2), as applicable, and quality (see 3.6) are acceptance tests and shall be performed on each lot.

#### 4.2.2 Periodic Tests

Cleaning and processing solution tests (see 8.5) to ensure that the anodic coating will conform to specified requirements are periodic tests and shall be performed at a frequency selected by the processor unless frequency of testing is specified by the cognizant quality organization.

#### 4.2.3 Preproduction Tests

All technical requirements are preproduction tests and shall be performed prior to or on the initial shipment of processed parts to a purchaser, when a change in material and/or processing requires approval by the cognizant engineering organization (see 4.4.2), and when the purchaser and/or cognizant engineering organization deems confirmatory testing to be required.

### 4.3 Sampling

Shall be not less than the following: a lot is a group of parts, all of the same part number, processed through the same chemical solutions in the same tanks under the same conditions, which have completed the chemical processing within a period of 24 hours of each other and are presented to inspection at the same time.

#### 4.3.1 For Acceptance Tests

Shall be as shown in Table 3.

**Table 3 - Sampling for acceptance testing**

Number of Parts in Lot	Quantity	Coating Weight or Coating Thickness As Applicable
Up to 7	All	3
8 to 15	7	4
16 to 40	10	4
41 to 110	15	5
111 to 300	25	6
301 to 500	35	7
Over 500	50	8

#### 4.3.2 For Periodic Tests

Sample quantity and frequency shall be selected at the discretion of the processor, unless otherwise specified.

#### 4.3.3 Coating Thickness and Coating Weight

Shall be determined on representative parts when size and shape permit accurate determinations. If parts are of such size and shape that accurate determination cannot readily be made, coating thickness and coating weight tests shall be made on separate specimens, having surface area not less than 24 square inches ( $155 \text{ cm}^2$ ), made of the same generic class of alloy as the parts represented. Separate specimens, if used, shall be processed with the parts they represent. In case of dispute, results of tests on actual parts shall govern.

### 4.4 Approval

4.4.1 The process and control procedures, a reproduction sample, or both, whichever is specified, shall be approved by the cognizant engineering organization before production parts are supplied.

4.4.2 The processor shall make no significant change to materials, processes, or control factors from those on which the approval was based, unless the change is approved by the cognizant engineering organization. A significant change is one which, in the judgment of the cognizant engineering organization, could affect the properties or performance of the parts.

4.4.2.1 Control factors for the process shall include, but not be limited to, the following:

Cleaning procedure

Composition limits for electrolyte

Electrolyte operating temperature and limits

Racking setup

Coating current density

Current density limits

Sealer composition limits

Thickness determination method

Periodic test plan

### 4.5 Reports

The processor of coated parts shall furnish with each shipment a report stating that the parts have been processed and tested in accordance with specified requirements and that they conform to the acceptance test requirements. The report shall include the purchase order number, lot number, AMS2478F, part number, and quantity.