

**ADOPTION NOTICE**

SAE-AMS5582, "NICKEL ALLOY, CORROSION AND HEAT RESISTANT, SEAMLESS TUBING 72NI - 15.5CR - 0.95 CB - 2.5TI - 0.70A1 - 7.0FE ANNEALED", was adopted on 10-MAR-89 for use by the Department of Defense (DoD). Proposed changes by DoD activities must be submitted to the DoD Adopting Activity: ASC/ENOI, Building 560, 2530 Loop Road West, Wright-Patterson AFB, OH 45433-7101. Copies of this document may be purchased from the Society of Automotive Engineers 400 Commonwealth Drive Warrendale, Pennsylvania, United States, 15096-0001. <http://www.sae.org/>

**Custodians:**

Army - MR  
Navy - AS  
Air Force - 11

**Adopting Activity:**

Air Force - 11

SAENORM.COM: Click to view the full PDF of SAEAMS5582d

**FSC 4710**

**DISTRIBUTION STATEMENT A:** Approved for public release; distribution is unlimited.



400 Commonwealth Drive, Warrendale, PA 15096-0001

# AEROSPACE MATERIAL SPECIFICATION



AMS 5582D

Issued JUN 1959  
Revised DEC 1995

Superseding AMS 5582C

Submitted for recognition as an American National Standard

Nickel Alloy, Corrosion and Heat Resistant, Seamless Tubing

72Ni - 15.5 Cr - 0.95Cb - 2.5Ti - 0.70Al - 7.0Fe

Annealed

UNS N07750

## 1. SCOPE:

### 1.1 Form:

This specification covers a corrosion and heat resistant nickel alloy in the form of seamless tubing.

### 1.2 Application:

This tubing has been used typically for fluid lines requiring high strength up to 1300 °F (704 °C) and oxidation resistance up to 1800 °F (982 °C), but usage is not limited to such applications. Parts may be formed and then heat treated to improve strength at elevated temperatures.

## 2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

### 2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

|          |   |
|----------|---|
| AMS 2263 | Tolerances, Nickel, Nickel Alloy, and Cobalt Alloy Tubing   |
| MAM 2263 | Tolerances, Metric, Nickel, Nickel Alloy, and Cobalt Alloy Tubing   |
| AMS 2269 | Chemical Check Analysis Limits, Nickel, Nickel Alloys, and Cobalt Alloys  |
| AMS 2371 | Quality Assurance Sampling and Testing, Corrosion and Heat Resistant Steels and Alloys, Wrought Products and Forging Stock            |
| AMS 2634 | Ultrasonic Inspection, Thin Wall Metal Tubing   |
| AMS 2807 | Identification, Carbon and Low-Alloy Steels, Corrosion and Heat Resistant Steels and Alloys, Sheet, Strip, Plate, and Aircraft Tubing |

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 1998 Society of Automotive Engineers, Inc.  
All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:  
TO PLACE A DOCUMENT ORDER:

(724) 772-7154  
(724) 776-4970  
<http://www.sae.org>

FAX: (724) 776-0243  
FAX: (724) 776-0790

Distributed under license from the IHS Archive

## 2.2 ASTM Publications:

Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

- ASTM E 8 Tension Testing of Metallic Materials
- ASTM E 8M Tension Testing of Metallic Materials (Metric)
- ASTM E 112 Determining the Average Grain Size
- ASTM E 354 Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys
- ASTM E 426 Electromagnetic (Eddy-Current) Testing of Seamless and Welded Tubular Products, Austenitic Stainless Steel and Similar Alloys
- ASTM E 1417 Liquid Penetrant Examination

## 2.3 U.S. Government Publications:

Available from DODSSP, Subscription Services Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.

MIL-STD-163 Steel Mill Products, Preparation for Shipment and Storage

## 3. TECHNICAL REQUIREMENTS:

### 3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 354, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

| Element          | min   | max   |
|------------------|-------|-------|
| Carbon           | --    | 0.08  |
| Manganese        | --    | 1.00  |
| Silicon          | --    | 0.50  |
| Sulfur           | --    | 0.010 |
| Chromium         | 14.00 | 17.00 |
| Nickel           | 70.00 | --    |
| Columbium        | 0.70  | 1.20  |
| Titanium         | 2.25  | 2.75  |
| Aluminum         | 0.40  | 1.00  |
| Iron             | 5.00  | 9.00  |
| Cobalt (3.1.1)   | --    | 1.00  |
| Tantalum (3.1.1) | --    | 0.05  |
| Copper           | --    | 0.50  |

3.1.1 Determination not required for routine acceptance.

3.1.2 Check Analysis: Composition variations shall meet the requirements of AMS 2269.

3.2 Condition:

Bright annealed or annealed and descaled. Cooling from the annealing temperature shall be at a rate equivalent to an air cool or faster.

3.3 Fabrication:

Tubing shall be produced by a seamless process.

3.4 Properties:

Tubing 0.125 inch (3.18 mm) and over in nominal OD and 0.015 inch (0.38 mm) and over in nominal wall thickness shall conform to the following requirements.

3.4.1 As Annealed:

3.4.1.1 Tensile Properties: Shall be as shown in Table 2, determined in accordance with ASTM E 8 or ASTM E 8M.

TABLE 2 - Tensile Properties

| Property  | Value              |
|---|--------------------|
| Tensile Strength, maximum                       | 140 ksi (965 MPa)  |
| Yield Strength at 0.2% Offset, maximum          | 80.0 ksi (552 MPa) |
| Elongation in 2 inches (50.8 mm) or 4D, minimum |                    |
| Strip Specimen                                  | 30%                |
| Full Tube                                       | 35%                |

3.4.1.2 Average Grain Size: Shall be ASTM No. 2.5 or finer, determined in accordance with ASTM E 112.

3.4.1.3 Flarability: Specimens as in 4.3.1 from tubing 0.188 to 2.000 inches (4.78 to 50.80 mm), inclusive, in nominal OD shall withstand flaring at room temperature, without formation of cracks or other visible defects, by being forced axially with steady pressure over a hardened and polished tapered steel pin having a 74-degree included angle to produce a flare having a permanent expanded OD not less than 1.20 times the original nominal OD.

3.4.2 After Precipitation Heat Treatment: Tubing shall have the following properties after being precipitation heat treated by heating to  $1300^{\circ}\text{F} \pm 25$  ( $704^{\circ}\text{C} \pm 14$ ), holding at heat for 20 hours  $\pm 1$ , and cooling in air:

3.4.2.1 Tensile Properties: Shall be as shown in Table 3, determined in accordance with ASTM E 8 or ASTM E 8M.

TABLE 3 - Minimum Tensile Properties

| Property                               | Value              |
|--|--------------------|
| Tensile Strength                       | 155 ksi (1069 MPa) |
| Yield Strength at 0.2% Offset          | 100 ksi ( 689 MPa) |
| Elongation in 2 Inches (50.8 mm) or 4D |                    |
| Strip Specimen                         | 15%                |
| Full Tube                              | 20%                |

3.5 Quality:

Tubing, as received by purchaser, shall be uniform in quality and condition and shall have a finish conforming to the best practice for high quality aircraft tubing. It shall be smooth and free from heavy scale or oxide, burrs, seams, tears, cracks, grooves, laminations, slivers, pits, and other imperfections detrimental to usage of the tubing. Surface imperfections, such as handling marks, straightening marks, light mandrel and die marks, shallow pits, and scale pattern, will not be considered injurious if the imperfections are removable within the tolerances specified for wall thickness but removal of such imperfections is not required.

3.5.1 Tubing shall be free from grease or other foreign matter. Metallic flakes or particles shall not be collected on a clean white cloth drawn through the length of the bore of a test sample. Discoloration of the cloth, without the presence of flakes or particles, is acceptable.

3.5.2 When specified by purchaser, tubing shall be subjected to fluorescent penetrant inspection in accordance with ASTM E 1417, to ultrasonic inspection in accordance with AMS 2634, to electromagnetic (eddy-current) inspection in accordance with ASTM E 426, or to any combination thereof. Tubing shall meet the requirements of 3.5 and other acceptance criteria established by the cognizant engineering organization.

3.6 Tolerances:

Shall conform to all applicable requirements of AMS 2263 or MAM 2263.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of tubing shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the tubing conforms to the requirements of this specification.